

Received: 11/30/2010 Completed: 11/30/2010 Letter: L rb P.O.#: Test Report #: 2-85546-0-RV

Client's Identification Product Name: UltraCanvas Artist C325. 100% Woven Polyester with Biodegradable Water Base Coating Front and Back Side. End Use of Product: Digital Graphics.

Tested For: **Dwight Bessette** Key Test: NFPA 701-89 Sm NC RVNC
Ultraflex Systems Inc. Tel: 1-(973)-664-6724 Ext:
1578 Sussex Tpk., Bldg. #4 Fax: 1-(973)-627-8506
Randolph, NJ 07869

PC: 1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Resistant Textiles and Films 1989 Edition (Small Scale Procedure for Curtains & Draperies Weighing Less than 10 oz/yd²)

Note: NFPA 701 - 1989 Edition was specified by the older building codes for draperies, window treatments, and similar hanging decorations. The older building codes required both the Small Scale and Large Scale Tests.

In 1996 NFPA 701 was revised and an entirely different test was developed for draperies, window treatments, and similar hanging decorations. This single test (which replaces the 1989 Tests) is designated as Test Method 1.

RESULTS REPORTED: Initially
 After 3 dry cleanings
 After 5 launderings @ 160°F

RESULTS:	Specimen #	Afterflame* (seconds)	Flaming Drip (seconds)	Char Length (inches)
Length:	1	0.0	1.0	4.0
	2	30.0+	3.0	5.9
	3	30.0+	2.6	4.2
	4	5.3	1.7	4.6
	5	4.7	2.3	4.1
Width:	6	13.2	0.6	5.6
	7	0.0	3.5	2.6
	8	10.1	2.2	4.8
	9	30.0+	0.0	5.4
	10	16.2	0.0	5.2
			-----	-----
			Avg: 1.7	Avg: 4.6

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 9.7 oz/yd²

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

Complies; Does not comply; Requires testing of 5 additional specimens

Received: 11/30/2010	Completed: 11/30/2010	Letter: L	rb	P.O.#:	Test Report #:	2-85546-0-RV
----------------------	-----------------------	-----------	----	--------	----------------	--------------

Client's Identification	Product Name: UltraCanvas Artist C325. 100% Woven Polyester with Biodegradable Water Base Coating Front and Back Side. End Use of Product: Digital Graphics.
-------------------------	--

Tested For: Dwight Bessette Ultraflex Systems Inc. 1578 Sussex Tpk., Bldg. #4 Randolph, NJ 07869	Key Test: NFPA 701-89 Sm NC RVNC Tel: 1-(973)-664-6724 Fax: 1-(973)-627-8506	Ext:
--	--	------

ACCEPTANCE CRITERIA:

Afterflame (seconds)	Flaming Drip (seconds) Maximum Average	Char Length (inches)	
		Max. Avg.	Max. Ind. Spec.
*	2.0	6.5"	7.5"


* Afterflame is required to be recorded;
however, it is not factored into the Acceptance Criteria.

RETEST PROVISION:

Test 5 additional specimens if only 1 specimen exceeds 7.5" Char Length.

REMARKS: None.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 1989 Edition Small Scale Procedure for Curtains and Draperies.


Robert I. Brown

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. / ec

NOV 17 2010

RV.12.10.10